

Produktspezifikation

Artikel # 64

Kraftpapier, maschinenglatt, braun, ca. 70 g/m², Secarerolle: 50 cm,
 Rollendurchmesser: 20-22 cm, Hülse: 5,0 cm

Unser Lieferant übermittelt uns folgende Information im Originaltext:

| Parameter | Test method | Unit of measure | Substance (g/m ²) |
|-----------------------------|--------------------|----------------------|-------------------------------|
| Moisture | ISO 287 | % | 7.8 |
| Bursting strength | ISO 2758 | kPa | 291 |
| SCT _{CD} | ISO 9895 | kN/m | 1.35 |
| TEA, MD/CD | ISO 1924-3 | J/m ² | 71/107 |
| TEA index, MD/CD | ISO 1924-3 | J/g | 1/1.5 |
| Tensile strength; MD/CD | ISO 1924-3 | kN/m | 6.9/2.8 |
| Tensile index, MD/CD | ISO 1924-3 | Nm/g | 100/39 |
| Stretch at break, MD/CD | ISO 1924-3 | % | 1.7/5.8 |
| Tear index, MD/CD | ISO 1974 | mN.m ² /g | 8.5/10.5 |
| Cobb ₆₀ (top) | ISO 535 | g/m ² | 30 |
| Cobb ₆₀ (bottom) | | | 50 |
| Dennison test | TAPPI 459 om-08 | No. | 18 |
| Gurley | ISO 5636-5 | s | 50 |

Typical values after conditioning measured at 50 ± 2% RH and 23 ± 1 °C
 (ISO 187:1990)

Valid: 31.12.2020 or until further notice

PAUL HILDEBRANDT AG

14.05.2020

Datum, Unterschrift

100244

use